## RECEIVED CENTRAL FAX CENTER

AUG 1 4 2006

## AMENDMENT TO THE CLAIMS

- 1. (currently amended) A nickel-metal hydride electrochemical cell, comprising:
- a positive electrode including a nickel-hydroxide active material;
- a negative electrode including a hydrogen storage alloy active material;
- a separator electrical insulating said positive electrode form from said negative electrode, said separator having a hi-pot resistance greater than 400 volts, and an ionic resistance less than 15 ohm-cm; and an alkaline electrolyte.
- 2.(original) The electrochemical cell of claim 1, wherein said separator has an absorbency between 30% and 50% relative to said alkaline electrolyte at 100 psi.
- 3. (original) The electrochemical cell of claim 1, wherein said separator has an absorbency between 35% and 48% relative to said alkaline electrolyte at 100 psi.
- 4. (original) The electrochemical cell of claim 1, wherein said separator has an absorbency between 38% and 46% relative to said alkaline electrolyte at 100 psi.

- PAGE 05/08
- 5. (original) The electrochemical cell of claim 1, wherein said separator has a hi-pot resistance greater than 500 volts.
- 6. (original) The electrochemical cell of claim 1, wherein said separator has an ionic resistance less than 12 ohms-cm.
- 7. (original) The electrochemical cell of claim 1, wherein said separator has an ionic resistance less than 10 ohm-cm.
- 8. (original) The electrochemical cell of claim 1, wherein said alkaline electrolyte is an aqueous solution of an alkali metal hydroxide.
- 9. (original) The electrochemical cell of claim 8, wherein said alkali metal hydroxide comprises potassium hydroxide, lithium hydroxide or sodium hydroxide.